

BamBüPly™



How to Work with Bamboo Plywood

Questions? (844) 293-6060 - www.Bamboo-Design.ca

BamBüPly™ Bamboo Plywood

Natural beauty, exceptional strength, and environmental responsibility.

The following information applies to BamBüPly™ bamboo plywood from Bamboo Design & Architecture, all of which can be used for various applications in diverse environments such as kitchens or bathrooms, furniture of all kinds, wall applications or other similar applications, both residential and commercial.

Before you Begin

Before starting your cabinetry project, it is essential to thoroughly inspect your panel to ensure it has not been damaged during transport and that the delivered goods conform to your order. It is natural and normal to find variation in the color of the bamboo grain, and this does not represent a manufacturing defect. To this end, all panels to be used should be grouped according to their color for the best result.

Bamboo, although a grass, reacts like hardwood and can be affected by environmental changes. The following basic steps for handling, fabrication, and installation are recommended to avoid or minimize certain problems related to wood movement.

Handling

- **Minimizing Handling** - This is the best way to reduce damage. Plan storage and processing operations to eliminate excessive handling.
- **Horizontal transport**- Support panels when transporting horizontally to avoid material stress.

Storage

1. **Store properly** - Panels should be stored flat on raised battens of equal thickness. Keep similar lengths of similar products together and maintain proper alignment between them to avoid bending the panels.
2. **Temperature** - Avoid extremes of heat and cold. Panels should be stored indoors. Ideal temperatures are between 18°C and 24°C (64°F to 75°F).
3. **Humidity** - Avoid extremes of humidity. Store away from water and off concrete floors. Humidity controls should be installed and maintained at a constant relative humidity between 35% and 65%. The relative humidity of the storage environment should mimic that of the intended installation environment.

Extremely dry climates or environments that cannot maintain a constant relative humidity between 35% and 65% year-round are not appropriate environments. Very damp environments where material will come in contact with extreme moisture or water are also not appropriate for storage.

Acclimation

BamBüPly™ bamboo panels are manufactured with an average moisture content of 6 to 9%. However, due to environmental conditions, the product you receive may vary. It is recommended to take a moisture reading before working with a panel. If acclimatization is necessary, it should be done before working the material and should take into account the environment and application at the final installation point.

BamBüPly™ bamboo panels, like wood products, expand and contract with changes in relative humidity (RH). The greater the seasonal variation, the greater the potential for movement.

For optimal performance, a temperature of 45 to 75 degrees Fahrenheit (10 to 24 degrees Celsius) and a relative humidity of 35% to 65% should be maintained throughout the year. Any cabinetmaker should acclimate their materials based on their understanding and knowledge of the final environment where the project will be installed. Failure to meet these objectives may create undesired movements in the panels, including cracking, splitting, and warping in some cases.

1. Remove the plastic wrapping that protects the bamboo panels to be cut;
2. Lay the bamboo panels flat, horizontally, while adding spacers between each of them to allow air circulation;
3. Ensure that the panels are left in this position without their plastic wrapping and with spacers between each of them until the relative humidity of the room where the panels will be worked is reached.

Working with BamBüPly™ Bamboo Plywood

Understanding Bamboo Panel Construction

3-Ply Cross-Laminated Structure

The most common structure used since 1996 remains undoubtedly the 3-ply construction. Like all cross-ply constructions, it is designed for greater stability. This construction uses a perpendicular core across the entire width of the panel and consists of multiple narrow full-length bamboo strips, laminated side by side into a single central panel. The surface plies are assembled similarly but with a grain running from bottom to top along the length of the panel, completing the 3-ply cross-laminated structure.

The three-ply cross-laminated construction is also the most popular for its versatility of application. Uses for this panel include cabinetry, shelving, kitchen or bathroom cabinets, store displays, furniture, and wall panel systems.

Single-Ply Linear Structure

Single-ply laminated panels will function similarly to a solid wood product. They are crafted from 1/4" thick (edge) and 3/4" wide (face) strips. Multiple strips are laminated face to face (the 3/4" face), so that when the panel is fully assembled, the visible surface shows only the 1/4" edge of the bamboo strip, giving it its distinctive linear appearance. The single-ply presents a linear grain running along the length of the panel without cross-plying.

Single-ply structured panels will generally be cut into narrower pieces, serving more as solid lumber products necessary for furniture making, cabinet door frame construction, or other applications where the panel needs to be well secured and supported.

*As these panels do not have a cross-ply core, this product is not recommended for single-piece cabinet doors.

Tools

BamBüPly™ Bamboo plywood can be worked using the same techniques and equipment as the cabinetry industry, including hand and workshop tools as well as CNC machines. If you need to work the material in an unconventional way and are not sure of the result you will obtain, first perform a test to confirm your working method and its compatibility with the product.

Adhesives and Assembly Methods

BamBüPly™ bamboo panels work well with most fastening methods currently used in the cabinetmaking industry. Note, however, that due to the superior hardness of bamboo, it will be necessary to pre-drill the structure using a drill before screwing. Consequently, nails and hammers should be avoided.

All types of glues are compatible with our bamboo panels.

Sanding

BamBüPly™ bamboo panels, like conventional wood, can be sanded using the same conventional cabinetmaking materials and equipment, including traditional sandpaper, hand sanders, or industrial sanding equipment.

Finishing

BamBüPly™ bamboo panels can be finished using conventional methods and products, including hand rubbing, spraying, brushing, industrial roller, or industrial equipment combined with a continuous UV varnishing system.

All regular finishes will generally work well with BamBüPly™ bamboo panels, but it is always prudent to verify their compatibility by performing a test on a small sample beforehand. Since we cannot verify the compatibility of all finishing techniques available on the market, the responsibility for ensuring the compatibility of the finish ultimately lies with the user.

1. **Finishing on all sides** - All surfaces must be finished, including edges, ends, cutouts, and the underside. The longer a panel is left unfinished in changing environmental conditions, the higher the chances it will develop instability issues. This is a normal and natural reaction of any material due to variable environmental conditions and is not considered a manufacturing defect.
2. **Apply a sealer** - It is recommended to apply a sealer to all surfaces of the panel before applying your finish to better protect the material against moisture. Several layers of sealer on the end grain are desirable for thorough and effective sealing. An even application of sealer and finish is recommended on all surfaces to allow for perfect balancing of materials. For example, if two full coats are applied to an upper face, two full coats of the same finish should be applied to the opposite face. Any new cut must be resealed.
3. **Thoroughly dry sealers** - Ensure sealers and finishes are thoroughly dried between each application and maintain relative humidity between 35% to 65% throughout the year.

Maintenance and Care of your BamBüPly™ Bamboo Panels

BamBüPly™ architectural grade bamboo panel should be maintained like a quality piece of furniture.

Daily Cleaning

- Regular cleaning is best done with a soft, lint-free cloth slightly dampened with water or a microfiber cloth to attract dust.
- No abrasives, chemicals, or ammonia-based cleaners should be used to clean quality wood surfaces.
- For stubborn stains, use mild soap and lukewarm water. Avoid ammonia-based cleaners.
- Dry immediately after cleaning to prevent water absorption.

Regular Maintenance

- Clean up spills immediately to avoid stains and moisture infiltration.
- Avoid excessive or repetitive impacts, even if lightly applied. The cellular structure of bamboo will compress under pressure.
- Avoid high localized heat, such as a hot pan or plate, or a hot light source, near or in contact with the finished surface. Direct sunlight exposure will alter the appearance of bamboo/wood over time.
- Maintain relative humidity around bamboo panels to minimize movement. A relative humidity between 35% and 65% is recommended.

Repair

- Light scratches can be sanded with fine sandpaper, following the grain of the bamboo.
- For more significant damage, consult a professional.

Additional Notes

Bamboo plywood is designed for indoor use only. Bamboo Design cannot be held responsible for inappropriate applications or structural variations of materials due to inadequate environmental conditions.

If you have any other questions about a specific product or application, please don't hesitate to contact us for more information.

Toll-free number: (844) 293-6060 or email us at info@bamboo-design.ca.

BamBüPly™ Bamboo Plywood Technical Information

Available Dimensions:	96" x 48" x 3mm, 5-ply – (2440 x 1220 x 3mm) 96" x 48" x 1/4", 3-ply – (2440 x 1220 x 7mm) 96" x 48" x 1/2", 3-ply – (2440 x 1220 x 12mm) 96" x 48" x 3/4", 3-ply – (2440 x 1220 x 19mm) 72" x 25" x 1.5", 5-ply – (1829 x 635 x 38mm) 96" x 25" x 1.5", 5-ply – (2440 x 635 x 38mm) 96" x 36" x 1.5", 5-ply – (2440 x 914 x 38mm) 96" x 48" x 1.5", 5-ply – (2440 x 1220 x 38mm)
Construction :	Cross-ply, full-length strips
Certifications :	CARB II and FSC 100% upon request.
Adhesive:	Architectural Grade, ULEF (Ultra Low Emitting Formaldehyde) No Added Formaldehyde
Wood Grade :	Architectural – Cabinetry Quality
Finish :	Unfinished
Hardness :	25% Harder than Maple
Fire Resistance:	Fire Resistance Classification: Class C According to ASTM E 84 standard Class B available upon request.
Warranty:	Residential: 5 years from date of purchase Commercial: 1 year from date of purchase
LEED® Credit :	ULEF, (Ultra Low Emitting Formaldehyde) IEQc4.4: Low-Emitting Materials MRc6: Rapidly Renewable Resource MRc7: Certified Wood
Weight :	96" x 48" x 3mm - 15 lbs (6.80 kg) 96" x 48" x 1/4" - 35 lbs (15.88 kg) 96" x 48" x 1/2" - 65 lbs (29.48 kg) 96" x 48" x 3/4" - 90 lbs (40.82 kg) 72" x 25" x 1.5" - 68 lbs (30.84 kg) 96" x 25" x 1.5" - 90 lbs (40.82 kg) 96" x 36" x 1.5" - 130 lbs (58.97 kg) 96" x 48" x 1.5" - 175 lbs (79.38 kg)

For more information, please contact us.

Toll-free: (844) 293-6060 or email us at info@bamboo-design.ca.